



TECHNICAL INFORMATION

TIVAR® H.O.T.

(Higher Operating Temperature)

Meets requirements of FDA regulation 21CFR 177.1520, item 2.1 and 2.2, for articles intended for direct and indirect food contact usage and regulation 21CFR 178.2010 governing additives and food contact usage.


Physical Properties

Property	Method	SI Unit	SI Value	English Unit	English Value
Yield Point	ASTM D-638	MPa	19.8	psi	2873
Elongation at Break	ASTM D-638	%	200	%	200
Tensile Break	ASTM D-638	MPa	52.5	psi	7618
Izod Impact	ASTM D-4020	kJ/m ²	60	ft-lbs/in ²	29
Static Friction	ASTM D-1894	Unitless	0.15	Unitless	0.15
Dynamic Friction	ASTM D-1894	Unitless	0.12	Unitless	0.12
Coefficient of Thermal Exp.	ASTM D-696	°C ⁻¹	0.0002	°F ⁻¹	0.00011
Melt Point	ASTM D-3417	°C	137-143	°F	278-289
Maximum Operating Temp.		°C	135	°F	275
Water Absorption	ASTM D-570	%	nil	%	nil


* Values are averages and are not specifications.

** ASTM test methods are under current procedures.


IMPORTANT: Most plastics will ignite and sustain flame under certain conditions. Caution is urged where any material may be exposed to open flame or heat-generating equipment. Use [Material Safety Data Sheets](#) to determine auto-ignition and flashpoint temperatures of materials, or consult Poly Hi Solidur, Fort Wayne, Indiana if additional information is needed. The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Poly Hi Solidur, Inc. shall not be liable and the customer assumes all risk and liability of any use or handling of any material beyond Poly Hi Solidur's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.



Dotted line represents TIVAR® H.O.T.
Solid line represents standard UHMW-PE



Dotted line represents TIVAR® H.O.T.
Solid line represents standard UHMW-PE



Note: In the Abrasion Index, the lower the number the better.
Dotted line represents TIVAR® H.O.T.
Solid line represents standard UHMW-PE

