

New York

Philadelphia

Atlanta

Chicago

Los Angeles

Fachbach, Germany



UNIFONE® PSO

UNIFONE PSO (Polysulfone) is an amorphous high performance thermoplastic that has proven performance at elevated temperatures. Good mechanical properties along with thermal stability allow for its use in load bearing applications over broad temperature ranges. Other notable attributes include flame retardance, excellent radiation resistance, and good chemical resistance. The ability of UNIFONE PSO to withstand common sterilization techniques supports its use in numerous sanitary applications such as medical instruments and food processing machinery.

Nytef Plastic's UNIFONE PSO stock shapes are amber in color and semi-transparent. They machine easily and are available in a full range of heavy gauge rod, plate and tubular bar sizes.

PRODUCT ATTRIBUTES

- 320°F Continuous Use Temperature
- Excellent Strength and Rigidity, Even at Elevated Temperatures
- High Impact Resistance
- Low Moisture Absorption
- Chemically Resistant to Many Acids and Solvents
- Superior Electrical Properties
- Rated UL V-0

- Gamma Radiation Resistance
- Easily Machined and Fabricated

INDUSTRIES

- Medical
- Pharmaceutical Manufacturing
- Aircraft and Aerospace
- Appliance Manufacturing
- Electrical and Electronics Manufacturing
- Food Processing

APPLICATIONS

- Manifolds
- Electrical Insulators, Connectors, and Components
- Aircraft Instrumentation
- Medical Instruments and Instrument Trays
- Sensors and Analytical Instruments
- Microwave Cookware

Nytef Plastics, Ltd. is dedicated to supplying our customers with the highest quality thermoplastic stock shapes for machining. We manufacture and stock a full line of thermoplastic materials in a wide variety of rod, plate and tubular bar sizes. In addition, we offer over 30 years of experience in the custom extrusion of application-specific and proprietary resins to meet even the most demanding performance requirements. Nytef Plastics offers full technical support for all products and is certified to ISO 9002 standards for the manufacture of extruded plastics stock shapes.

UNIFONE® POLYSULFONE

Property	Test Method	Units	UNIFONE® Polysulfone
Mechanical			
Specific Gravity	ASTM-D792	_	1.24
Tensile Strength	ASTM-D638	psi	10,200
Tensile Elongation	ASTM-D638	%	50
Tensile Modulus of Elasticity	ASTM-D638	psi	360,000
Flexural Strength	ASTM-D790	psi	15,400
Flexural Modulus of Elasticity	ASTM-D790	psi	390,000
Izod Notched Impact	ASTM-D256	ftlbs./in.	1.3
Rockwell Hardness	ASTM-D785	M scale	M82
Thermal			
Coef. of Linear Thermal Expansion	ASTM-D696	in./in./°F	3.2 x 10⁻⁵
Max. Continuous Use Temp.	Nytef std.	°F	320
Heat Deflection Temp. @ 264 psi	ASTM-D648	°F	345
Glass Transition Temperature	ASTM-D3418	°F	374
Melting Point	ASTM-D789	°F	650-750
Electrical			
Dielectric Strength – Short Term	ASTM-D149	volts/mil	425
Dielectric Constant @ 60 Hz	ASTM-D150		3.07
Dielectric Constant @ 106 Hz	ASTM-D150		3.03
Dissipation Factor @ 60 Hz	ASTM-D150		0.0008
Volume Resistivity	ASTM-D257	ohm-cm	> 10 ¹⁶
Miscellaneous			
Water Absorption/24 hrs.	ASTM-D570	% weight	0.3
Water Absortion @ saturation	ASTM-D570	% weight	0.6
Flammability	UL 94		V-0
Color			Amber
Agency Approvals			
FDA/USDA			Yes
3-A Dairy Standards			Yes
NSF Std. 61			Yes
USP Class VI			Yes

Nytef Plastics, Ltd. believes that all physical property data and other technical information and specifications contained in this document are the best available on the product or material at the time of publication. However, this information is intended merely as a guideline to performance. Persons intending to use this information or specifications should first satisfy themselves that the products and their features/properties are suitable for their intended uses and applications and meet all appropriate safety, health or other applicable standards. Nytef Plastics, Ltd. does not guarantee the effectiveness or safety of any possible or suggested design for articles of manufacture as illustrated herein by any photograph, technical drawing or the like. It is the end user's sole responsibility to performance test the finished part in the actual or intended application. Nytef Plastics, Ltd. makes no guarantee as to this information's accuracy or completeness and will not assume any obligation or liability whatsoever for use of this information, specification or data. Nothing herein waives any of the seller's terms and conditions of sale. References to products not manufactured by Nytef Plastics, Ltd. are not intended as an endorsement of those products nor to suggest an unsuitability of other similar products. Statements containing possible suggested uses of the materials described herein are not to be construed as a license to operate under, or intended to suggest infringement of any existing patent.

